

Technical Data of Carbonized Fiber Packing

Antileak Model No.	Product Name	Construction	Service Range		
			Max. Temperature	Max. Pressure	Max. Velocity
2300	Carbonized Fiber Packing	Braided from carbonized fiber yarn	<260℃	2MPa	2~10 meters/sec
2301	Carbonized Fiber Packing resistant to high temperature	Braided from carbonized fiber yarn that treated with graphite particles	<650℃	2MPa	2~16 meters/sec
2301 A	Carbonized Fiber Packing reinforced with aramid corners	Braided from carbonized fiber yarn and reinforced with aramid fiber yarn corners	<260℃	2MPa	2~10 meters/sec